

**Porcelain / Direct Screen Printing and Decals
High Temperature Platinum**

Colour	Product	Precious Metal Content	ASTM-resistant microwave-resistant Sanitary Ware	Notes*
white	SG 34/209	32%		firing range 1180-1230°C / 2155-2245°F
white gold	PG 5848	36%		firing range 1200-1250°C / 2190-2280°F <i>new!</i>
white gold	PG 5853	31%		firing range 1180-1250°C / 2155-2280°F <i>new!</i>
white platinum	SG 16/209	32%		firing range 1180-1230°C / 2155-2245°F
white platinum	SG 35/209	32%		firing range 1180-1230°C / 2155-2245°F
platinum	SG 42/UV	32%		UV-curing, firing range 1180-1230°C / 2155-2245°F
rosé	PG 5821	32%		firing range 1200-1250°C / 2190-2280°F <i>new!</i>

* High temperature precious metal preparations need to be stirred well before use